

STELLITE® 31 ALLOY

TECHNICAL DATA

Nominal Composition (mass %) and Physical Properties

Co	Cr	W	C	Others	Hardness	Density	Melting Range
Base	26	7.5	.5	Ni, Fe, Si, Mo	20-35 HRC	8.61 g/cm ³ 0.311 lb/in ³	2445-2545°F 1340-1395 °C

Stellite® cobalt base alloys consist of complex carbides in an alloy matrix. They are resistant to wear, galling and corrosion and retain these properties at high temperatures. Their exceptional wear resistance is due mainly to the unique inherent characteristics of the hard carbide phase dispersed in a CoCr alloy matrix.

Description

Stellite® 31 is a cobalt-base, high-temperature superalloy having high tensile and creep properties in precision casting. It is superior in stress-rupture properties to most alloys commercially available, especially at 1700 and 1800°F. **Stellite® 31** is resistant to oxidizing and reducing atmospheres up to 1150°C (2100°F). Excellent resistance to thermal and mechanical shock. Mainly used in gas turbine engines in areas subject to hot gas erosion.

Corrosion Resistance

Stellite® alloy 31 is resistant to both oxidizing and reducing gases up to 2100 °F and hence prevents scaling of gas turbine components. This alloy has excellent resistance to nitric and phosphorus acids, and at room temperature to sulphuric acid. **Stellite® alloy 31** is superior to **Stellite® alloy 6** in hydrochloric acid. Exposure test coupons should be used to verify performance whenever possible due to variations resulting from temperature, pH concentrations and contaminants.

Wear

During sliding, hot metal-on-metal wear this alloy forms an adherent oxide film which helps to prevent adhesive transfer. This has been used to advantage in jet engine spacer bushings and burner can retaining nuts. **Stellite® alloy 31** is useful where thermal fatigue is combined with metal-on-metal wear and has been used successfully for metal working tools such as extrusion dies and drills used to tap metallurgical furnaces.

Finishing

Due to the rate of workhardening in the solution annealed condition, it is best to machine this alloy in the aged condition. The alloy can be machined by all common methods using carbide tools. Low speeds and a positive cut will help to avoid burnishing.

Nominal Thermal Expansion Coefficient (from 20°C/68°F to stated temperature)

	100°C (212°F)	200°C (392°F)	300°C (572°F)	400°C (752°F)	500°C (932°F)	600°C (1112°F)	700°C (1292°F)	800°C (1472°F)	900°C (1652°F)	1000°C (1832°F)
μ-inch/inch.°F	5.83	6.53	6.94	7.25	7.47	7.72	7.97	8.22	8.44	-

Nominal Tensile Properties at Room Temperature

	Ultimate Tensile Strength Rm		Yield Stress Rp(0.2%)		Elongation	Elastic Modulus	
	ksi	MPa	ksi	MPa	A(%)	ksi	GPa
Castings	107	740	63	430	10	30,000	207

Thermal and Electrical Properties

	Approximate value at Room Temperature
Thermal conductivity	102 Btu-in/hr/ft ² /°F
Electrical resistivity	38.2 μ-ohm.inch

Applications

The excellent high temperature properties of this alloy are exploited in gas turbine vanes, blades, bushings and spacers. Furnace working tools which require a combination of mechanical integrity and hot wear resistance.

Available forms

Cast components, weld rod and powder metallurgy components.

Specifications

AMS 5382, ASTM A567 GR 2, UNS R3031.

Stellite is a registered Trade Name of Deloro Stellite.

Deloro Stellite manufactures sophisticated alloys in the form of castings, powders, coatings, consumables, and machined parts that resist wear, corrosion, and abrasion. Information provided in this document is intended only for general guidance about Deloro Stellite products and is the best information in our possession at the time. Product users may request information about their individual use of our products, but Deloro Stellite does not warrant or guarantee this information in any way. Selection and purchase of Deloro Stellite products is the sole responsibility of the product user based on the suitability of each use. Individual applications must be fully evaluated by the user, including compliance with applicable laws, regulations, and non-infringement. Deloro Stellite cannot know or anticipate the many variables that affect individual product use and individual performance results may vary. For these reasons, Deloro Stellite does not warrant or guarantee advice or information in this document, assumes no liability regarding the same, and expressly disclaims any warranty of any kind, including any warranty of fitness for a particular purpose, regarding the same.



UK SALES OFFICE

Deloro Stellite
Cheney Manor Industrial Estate
Swindon SN2 2PW
UK

Tel: (+44) 1793-498500
Fax: (+44) 1793-498501

E-Mail: saleshad@stellite.com

Literature Number:461-31
Copyright © 2008 Deloro Stellite
Printed in USA

www.stellite.com

US SALES OFFICE

Stellite Coatings
1201 Eisenhower Drive North
Goshen, Indiana 46526
USA

Tel: (+1) 574-534-2585
Fax: (+1) 574-534-3417

E-Mail: saleshad@stellite.com